



For high traffic areas that require a durable and easy to maintain surface, **OmniGuard** is the obvious choice. The high solid formulation of this UHS floor finish produces extreme gloss that withstands the effects of crowded market places in any weather condition.

## DIRECTIONS

Read all directions and Safety Data Sheets (SDS) before using.

1. For a floor that has been stripped, properly neutralized, rinsed and allowed to dry thoroughly, apply 4-5 thin coats using a clean synthetic mop. Allow the floor to dry thoroughly between coats and prior to burnishing.
2. Optional: Apply 2 thin coats of floor sealer for old or porous floors or for high traffic areas, then apply 2-3 coats of finish.
3. For a floor that has been deep scrubbed and allowed to dry thoroughly, apply 1-2 thin coats using a clean synthetic mop. Allow floor to dry thoroughly between coats and prior to burnishing.

## PRODUCT INFO

Product Code	141FS	141FSE	141MPE	141DR
Volume	2.50 US gallons	10 liters	4 liters	55 US gallons
Shipping Package	2 x 2.5 gallons	2 x 10 liters	4 x 4 liters	per unit
Pallet Quantity	48	48	48	4

## SURFACES



## TECHNICAL DATA

<b>Description</b>	Polymer emulsion
<b>Appearance</b>	Milky white
<b>Specular Gloss (60°)</b> ASTM D1455-87 (2008)	>85
<b>Viscosity (Brookfield)</b> @ 68°F (20°C)	<10 centipoise
<b>Coverage Rate</b>	2500 to 3000 ft <sup>2</sup> /gal 61 to 74 m <sup>2</sup> /liter
<b>Dry Time</b>	About 25 minutes
<b>Buffability</b>	Excellent
<b>Removability</b> ASTM D1792-06	Excellent
<b>VOC</b> 40 CFR Part 59 Subpart C	0.06%
<b>Non-Volatile Solids</b> ASTM D2834-95 (2008)	25%
<b>Fragrance</b>	Mild odor, no fragrance added
<b>Slip Resistance</b> ULTM410	Meets requirements
<b>Shelf Life</b> ASTM D1791-93 (2008)	1 year
<b>Density</b> ASTM D1475-98 (2008)	8.5 lb/gal @ 68°F 1.03 kg/L @ 20°C
<b>Detergent Resistance</b> ASTM D3207-92 (2008)	Excellent
<b>Freeze/Thaw</b> ASTM D3209-93 (2008)	Passes 3 cycles
<b>Container</b>	2.5 US gal/9.5 L (FS packaging) 2.64 US gal/10 L (FSE packaging) 1.06 US gal/4 L (MPE packaging) 55 US gal/208 L (DR packaging)



Floor Coating and Finishing materials  
as to slip resistance only.

42E6